



Firebricks



Dineen Sales Ltd.

Manufactured from some of the finest fireclays in the world, these firebricks are designed for moderate duty service.

- Type Standard
- Method of Manufacture Semi Dry Pressed
- Al₂O₃ 38 – 40%
- Fe₂O₃ 1.0 – 1.8%
- Apparent Porosity 18% Max
- Bulk Density 2.2
- Cold Crushing Strength 40 MN/M²
- Permanent Linear Change ± 0.4%
- Refractoriness under Load 1430 °C
- PCE (Pyrometric Cone Equivalent) 1700 °C

Dineen Sales Ltd.

Wolfhill,
Athy,
Co. Kildare

Phone: (059) 8635557
Fax: (059) 8635655
E-mail: info@dineensales.com

Our firebricks are available in 230 x 114 x 75/50/25mm
We also stock Class A and Class B Engineering Bricks and stock bricks

***Note** The above values are typical, but do not constitute a specification*